

SHUMAN COMPOUND: DATA SHEET

DESCRIPTION: POLYETHYLENE 603 BLACK

OFFERS THIS COMBINATION OF PROPERTIES:
HIGH DENSITY, INJECTION MOLDING GRADES, GOOD CHEMICAL RESISTANCE

TYPICAL PROPERTIES

<u>DENSITY</u> (RANGE)	<u>VALUE</u> .952 +	<u>UNITS</u>	<u>TEST METHODS</u> ASTM D-1505
---------------------------	------------------------	--------------	------------------------------------

<u>MELT FLOW RATE</u> (RANGES)			
	2.0 - 3.9	GM/10 MIN.	ASTM D-1238
	4.0 - 5.9		
	6.0 - 9.9		
	10.0 - 14.9		
	15.0 - 18.0		

SUGGESTED PROCESSING CONDITIONS: 360° - 410°F

NOTICE: THE INFORMATION CONTAINED HEREIN IS BASED ON WHAT WE BELIEVE TO BE RELIABLE DATA, BUT SHUMAN MAKES NO WARRANTIES EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. BECAUSE SHUMAN HAS NO CONTROL OVER THE USE TO WHICH OTHERS MAY PUT THE PRODUCT, IT DOES NOT SUGGEST OR REPRESENT THAT THE SAME RESULTS AS THOSE REFERRED TO HEREIN WILL BE OBTAINED BY ANOTHER USER. EACH USER OF THE PRODUCT AND THE COMPOSITIONS MENTIONED HEREIN SHOULD MAKE HIS OWN TESTS PRIOR TO PURCHASE TO DETERMINE THE PRODUCT'S SUITABILITY FOR HIS OWN PARTICULAR USES.

NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A RECOMMENDATION FOR THE USE IN VIOLATION OF ANY EXISTING PATENT, FOREIGN OR DOMESTIC, OR OF APPLICABLE LAWS AND REGULATIONS.

REV01/03

DATA SHOWN ARE THE AVERAGE RESULTS OF OUR OWN TESTS AND SHOULD NOT BE USED FOR SPECIFICATIONS
